

PS-800 SUPER BONDING ADHESIVE VOC COMPLIANT FORMULATION

DESCRIPTION: Easy to use, fast curing, heavy-duty construction adhesive. Bonds most common building materials. VOC compliant.

USES:

Industries

- Construction
- Architectural
- Concrete
- Roofing

Substrates

- Wood
- Plywood
- Wolmanized lumber
- Concrete
- Metals
- Brick
- Gypsum
- Plaster

Not designed for continuous submersion or for use on polystyrene or polystyrene foams.

APPLICATION: Surfaces should be clean and free from oil, grease, water, dirt or any other material that may deter adhesion. Cut tip, puncture seal and insert in caulk gun. Apply adhesive to only one of the surfaces to be bonded. When bonding subfloors or wet, frozen and treated lumber, nail or screw as recommended by the American Plywood Association. Working time approximately 20-30 minutes for a 1/4" bead.

CLEANING: Scrape off dried excess with a putty knife. Remove residue with mineral spirits or equivalent solvent. Follow solvent vendor's precautions when using solvents. NOTE: Test solvent on an out-of-the-way area to make sure it will not mar or attack the surface.

SHELF LIFE: 12 months when properly stored.

FEATURES:

- High strength
- One part
- Excellent adhesion
- VOC compliant

BENEFITS:

- Durable bond to material
- No mixing and ready to use
- Bonds to most building surfaces
- Less than 50 g/L

STORAGE: Store tightly closed containers at 75° F. Will not freeze.

CAUTION: DANGER: EXTREMELY FLAMMABLE. VAPOR HARMFUL. Contains methyl acetate, hexane and acetone. Keep away from heat, sparks and flame. Use only with positive cross ventilation. Avoid breathing vapors. Do not swallow. Do not allow eye contact or prolonged skin contact. Uncured product can cause eye or skin irritation. Prolonged or repeated overexposure to solvents in uncured product can cause central nervous system, peripheral nervous system, eye, skin, liver, kidney or respiratory system effects.

First Aid: If dizziness or other adverse effects are experienced, move to fresh air; call physician if discomfort persists. If eye contact occurs, flush eyes with water for 15 minutes; contact physician immediately. If swallowed, do not induce vomiting; contact physician immediately. Wash skin contact areas with soap and water; contact physician if irritation persists. For additional information, refer to Material Safety Data Sheet. **KEEP OUT OF REACH OF CHILDREN.**

PACKAGING: 10.5 oz. tube.

COLOR: Tan.

SPECIFICATIONS:

Type	Synthetic elastomeric polymer
State	Medium viscosity mastic
Viscosity	130,000 CPS
VOC	<50 g/L
Weight/gallon	10.4 lbs
Flashpoint	Less than 0° F
Application temperature	0° F to 100° F
Service temperature	-20° F to 120° F

Exceeds the performance requirements of the American Plywood Association AFG-01 Specification, ASTM D3498 and C557, HUD/FHA Use of Materials Bulletin #60

All values are typical at 75° F, 50% R.H. unless otherwise noted